

Product Data Sheet

Updated: February 2010 Supersedes: April 2007

Product Description

Scotch-Weld EC40 is a low viscosity (40 cPs) Ethyl Cyanoacrylate based adhesive. EC40 is suitable for bonding a wide range of materials where fast cure speed is required.

Key Features

EC40 is specially formulated for high strength, general purpose bonding of most plastics, rubbers, metals and other common substrates. Recommended for use on assemblies with close fitting parts and smooth, even surfaces.

Physical Properties

| Base | Ethyl |
|------------------|---------------------------------|
| Soluble In | Acetone, MEK |
| Viscosity (cps) | Range 34-44 Typical Value 40 |
| Specific Gravity | 1.06 |
| Colour | Clear |

Performance Characteristics

| Maximum Gap Fill (best results are obtained with very thin bond lines) | 0.1mm |
|--|--|
| Fixture Time | 10-30secs |
| Tensile Strength (ISO 6922) | 20 N/mm ² |
| Full Cure | 24hrs |
| Speed of Cure | The speed of cure of cyanoacrylates varies according to the substrate to be bonded. Acidic surfaces such as paper and leather will have longer cure times than most plastics and rubbers |
| Moisture Resistance | Low resistance to high levels of moisture and humidity over time. |
| Service Temperature Range | -50 to +80°C |

Date: February 2010 Scotch-Weld Cyanoacrylate Adhesive EC40

Additional Product Information

Scotch-Weld Activators AC11 and AC12 may be used in conjunction with Scotch-Weld cyanoacrylates where cure speed needs to be accelerated. Cure speeds of less than 2 seconds can be obtained with most Scotch-Weld cyanoacrylates. The use of an activator can reduce the final bond strength by up to 30%.

Application Techniques

Bond speed is very fast so ensure that parts are properly aligned before bonding. Scotch-Weld Activators may be required if there are gaps or porous surfaces. Some plastics may require application of Scotch-Weld AC77 Primer. Ensure parts are clean, dry and free from oil and grease. Product is normally hand applied from the bottle. Apply sparingly to one surface and press parts firmly together until handling strength is achieved.

As a general rule, as little cyanoacrylate as possible should be used – over application will result in slow cure speed and lower bond strength.

Storage Conditions

Keep the adhesive in a cool, dry place away from direct sunlight. Under such conditions shelf life at room temperature will be 12 months.

Refrigeration to 5°C gives optimum storage stability.

Shelf Life

12 months from date of despatch by 3M when stored in the original carton at 21°C

Precautionary Information

Refer to product label and material Safety Data Sheet for health and safety information before using the product. For information please contact your local 3M Office.

www.3M.com

For Additional Information

To request additional information or to arrange for sales assistance, call 0870 6080050 Address correspondence to: 3M United Kingdom PLC, 3M House, 28 Great Jackson Street, Manchester, M15 4PA

Important Notice

All statements, technical information and recommendations contained in this document are based upon tests or experience that 3M believes are reliable. However, many factors beyond 3M's control can affect the use and performance of a 3M product in a particular application, including the conditions under which the product is used and the time and environmental conditions in which the product is expected to perform. Since these factors are uniquely within the user's knowledge and control, it is essential that the user evaluate the 3M product to determine whether it is fit for a particular purpose and suitable for the user's method or application. All questions of liability relating to this product are governed by the terms of the sale subject, where applicable, to the prevailing law.

Values presented have been determined by standard test methods and are average values not to be used for specification purposes. Our recommendations on the use of our products are based on tests believed to be reliable but we would ask that you conduct your own tests to determine their suitability for your applications.

This is because 3M cannot accept any responsibility or liability direct or consequential for loss or damage caused as a result of our recommendations

3M and Scotch-Weld are trademarks of the 3M Company.

3M United Kingdom PLC 3M House, 28 Great Jackson Street

28 Great Jackson Street, Manchester, M15 4PA Product Information :

Tel 0870 60 800 50 Fax 0870 60 700 99 3M Ireland Limited The Iveagh Building The Park, Carrickmines Dublin 18, Ireland Customer Service :

Tel (01) 280 3555 Fax (01) 280 3509