

BONDERITE M-AD BASE EP AERO

February 2021

PRODUCT DESCRIPTION

BONDERITE M-AD BASE EP AERO provides the following product characteristics:

Technology	Metal Pre-treatment
Product Type	Conversion Coating
Appearance	Viscous white liquid
Application Method	Brush
Application	Surface Treatment Process, Aviation Conversion Coating

BONDERITE M-AD BASE EP AERO is a thickening material formulated to enhance paint or varnish adhesion on vertical surfaces. It is specially designed to ease the application of chromate coatings on aluminum alloys.

TECHNICAL DATA

pH 6 to 8
Shelf Life @ 0 to +35 °C (in original package), days 730

GENERAL INFORMATION

Please consult the Safety Data Sheet (SDS) for safe handling information of this product.

DIRECTIONS FOR USE**Processing Equipments**

Containers for BONDERITE M-AD BASE EP AERO should be made of stainless steel, plastic, synthetic rubber or other acid resistant material.

Lead, tin, glass and galvanized iron containers are not suitable for this material.

Recommended Mix Ratios

Dissolve the required amount of chromate material listed below for every 1 kg of BONDERITE M-AD BASE EP AERO .

BONDERITE M-CR 1200 S AERO, grams	6 to 8
BONDERITE M-CR 1200 AERO, grams	16 to 20
BONDERITE M-CR 1500 AERO, mL	10

Mix continuously until material forms into a homogeneous, viscous paste. As soon as this consistency is reached, the chromate paste is ready to use.

Chromate Mixture Shelf Life

Although the resulting chromate mixture can be kept for a few days, it is, nevertheless, advised to only prepare a specified quantity needed for the work day.

Chromate mixture is best used before 24 hours after mixing. An upper layer can be observed with time which can easily emulsified.

Chromate Application Process

- Aluminum alloy surfaces to be chromated should be clean, dry and free from any contaminants that will affect adhesion. Deoxidize using BONDERITE C-IC 670 (10% solution) per manual application, by brush or wipe, at room temperature. Note that deoxidizing material concentration needs to be adjusted according to the fatty contamination level and/or oxide layer thickness.
- Allow deoxidizing material to stay for about 10 minutes. Carefully rinse off with water, using brush or spray. Allow surface to completely dry.
- Apply the chromate mixture using a brush.
- Reaction time is usually about 10 minutes under normal temperature conditions.
- Carefully rinse again with water, using brush or spray. Allow to completely dry.
- Regularly mix to keep the chromate mixture homogeneous throughout the chromate application process.
- Tightly close the container after application.

STORAGE AND HANDLING**Handling**

1. Solidification can happen by time (especially during extended storage at elevated temperatures).
2. Upper superficial solidification will not yield any negative effect to the performance of the product.
3. Re-mixing to homogenize the solution may be needed to prepare for further use.

Storage

Store in original, tightly covered containers in clean, dry areas. Storage information may be indicated on the product container labeling.

Optimal Storage: 0 to +35°C. Storage below 0°C can adversely affect product properties.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Henkel Representative.

Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.



Disclaimer

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product. Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

In case products are delivered by Henkel Corporation, or Henkel Canada Corporation, the following disclaimer is applicable:

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

Trademark usage

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1