TECHNICAL DATA SHEET

P.36 FLAME RETARDANT POLYESTER FILM TAPE



Saint-Gobain Tape Solutions

North America | South America | Europe | Asia For a full list of locations, please visit tapesolutions.saint-gobain.com/contact-us

General Description

23 micron polyester film coated with flame retardant acrylic adhesive. Designed for coil wrapping, interlayer insulation of electrical motors and transformers, wire harnesses. Excellent flagging and solvent resistance. Printable.

Features

- Good adhesion and conformability
- Printable
- Flame retardant UL 510

Technical Data

| Property | Value |
|-----------------------------------|---------------------|
| Product Type | Single coated |
| Backing Type | PET film |
| Adhesive Type | Modified acrylic |
| Color | White |
| Backing Thickness | 0,023 mm |
| Total Thickness | 0,068 mm |
| Peel Adhesion at 180° On Steel | 4.50 N/cm |
| Tensile Strength | 40.00 N/cm |
| Rolling Ball Tack | < 10 cm |
| Elongation at Break | 80% |
| Breakdown Voltage | 4.50 kV |
| Thermal Class | 130 (B) |
| Short Time Temperature Resistance | 180 °C |
| Flame Retardancy | Yes (UL 510) |
| Electrolitic Corrosion | 1 |
| Approvals | UL file No. E178430 |
| Shelf Life | 12 months |
| Standard Length | 66 m |
| Standard Width | 1000 mm |



* International harmonized test methods: ASTM D-1000, PSTC, EN 60454-2.

All statements and information listed above regarding this product are typical values for general guidance, these data have not to be intended as conformity specification. These suggestions are based on tests we believe reliable, but are not guaranteed for accuracy and completeness. The user must test, evaluate and validate this product before the use, assuming risks and liability of such use. This document may be revised without prior notice. Suggested storage temperature is between 10°C and 30°C with 50% relative humidity.

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain products for all intended uses and that the materials to be used comply with all applicable regulatory requirements. Saint-Gobain assumes no responsibility for any product failures that occur due to misuse of the materials it provides arising out of the design, fabrication or application of the products into which the materials are incorporated.

WARRANTY: For a period of 12 months, Saint-Gobain warrants this product(s) to be free from defects in manufacturing. The only obligation under any applicable product warranty will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. SAINT-GOBAIN DISCLAIMS ALL IMPLIED WARRANTIES OF MERCHANTABILITY AND FITNESS FOR A PARTICULAR PURPOSE.

Form #1817EU | © Saint-Gobain May 2021 | h-old is a trademark of Saint-Gobain.

SAINT-GOBAIN

Applications

- Motor & transformer manufacturers
- Capacitor manufacturers